

PRODUCT DATA SHEET

ALEX WAX 600

Date: 01/01/2023

Revision: 5

Properties	Test Method	Spec.	Typical value
------------	-------------	-------	---------------

Congealing Point,	[°C]	ASTM – D 938	60 – 64	62
Oil Content,	[%Wt]	ASTM – D 721	0.5 max	0.4
Penetration at 25°C	[mm/10]	ASTM – D 1321	16 – 20	19
Colour Saybolt		ASTM – D 156	+ 25 min	+27

Notice: This publication/data sheet and the information within were assembled and checked with utmost care and are to be regarded as accurate as of the date of issue. Nevertheless Alexandria Wax Products Co SAE (AWPC) takes no responsibility or warrant for its timeliness, completeness, quality or correctness. This publication/data sheet is for information only and doesn't warrant any particular product properties. It is the user's obligation to check the products and use them safely as well as to comply with all applicable laws and regulations.

AWPC shall not be responsible for any damage or injury in particular resulting from use, other than stated use of the material, from any failure to abide to recommendations, or from any dangers inherent in the nature of the material. It is recommended to contact the manufacturer for further information, especially if it is intended to use the product for applications other than stated. In addition the most recent version of our *General Terms of Sale* will apply.

Alexandria Wax Products Company

19 Kamal El Deen Salah St., El Salam Building, Smouha, Alexandria, Egypt.
Tel: (+203) 423 87 12/ 423 85 10/88 Fax: (+203) 423 84 26

A Joint Venture of

